

**PATENT ABSTRACTS OF JAPAN**(11)Publication number : **01-122970**(43)Date of publication of application : **16.05.1989**

(51)Int.Cl.

**C04B 35/58**  
**C22C 29/16**(21)Application number : **62-279625**(71)Applicant : **TOSHIBA TUNGALOY CO LTD**(22)Date of filing : **05.11.1987**(72)Inventor : **UCHIUMI YOSHIYUKI**  
**YAMAYA RYO****(54) CUBIC BORON NITRIDE SINTERED PRODUCT**

(57)Abstract:

PURPOSE: To obtain the above sintered product which is used as a cutting tool, because of its high abrasion resistance and high resistance to breaking-off, by combining cubic BN, AlN, AlB<sub>2</sub>, metal or alloy or Co and/or Ni as major components, Al<sub>2</sub>O<sub>3</sub> at a specific volume ratio and a metal compound of high melting point and calcining the mixture.

CONSTITUTION: Starting materials corresponding to 10W80vol.% of cubic BN of less than 15 $\mu$  average particle size; 1W5vol.% of AlB<sub>2</sub> and/or AlB<sub>12</sub>; 1W5vol.% of TiB<sub>2</sub>; 0.1W2vol.% of metal or its alloy containing mainly Co and/or Ni; 7.5W80vol.% of Al<sub>2</sub>O<sub>3</sub> of less than 1.0 $\mu$  average particle size in an amount corresponding to (0.5W0.956)/(0.5W0.044) volume ratio of Al<sub>2</sub>O<sub>3</sub>/the high melting metallic compound; and 3.75W40vol.% of high melting point metallic compound which is composed of at least one selected from carbides and nitrides of Ti, Zr, Hf, At, Nb or V, carbides of W and a solid solution containing the same, are mixed, crushed, formed then sintered at 1,300W1,600°C under a pressure of 40W60kb at 5W15min.

**LEGAL STATUS**

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]